

BLANK PAGE



Indian Standard

METHODS FOR CHEMICAL ANALYSIS OF CAST IRON AND PIG IRON

PART 4 DETERMINATION OF TOTAL CARBON, GRAPHITIC CARBON AND COMBINED CARBON BY GRAVIMETRIC METHOD

भारतीय मानक

ढलवां लोहे और कच्चे लोहे के रासायनिक विश्लेषण की पद्धतियां भाग 4 भारात्मक पद्धति द्वारा कूल कार्बन, ग्रेफाइटिक कार्बन और मिश्रित कार्बन ज्ञात करना

UDC 669·162·275·12+669·13:543·21 [543·842]

© BIS 1989

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

FOREWORD

This standard (Part 4) was adopted by the Bureau of Indian Standards on 17 October 1988, after the draft finalized by the Methods of Chemical Analysis of Ferrous Metals Sectional Committee had been approved by the Structural and Metals Division Council.

Chemical analysis of cast iron and pig iron was earlier covered in IS 228: 1959 'Methods of chemical analysis of pig iron, cast iron and plain carbon and low alloy steels (revised)'. During its second revision, it was decided that separate comprehensive series should be prepared, one for chemical analysis of all types of steels and the other covering chemical analysis of pig iron and cast iron. Accordingly, IS 228 on revision was published in several parts covering chemical analysis of various steels only, and a separate series of standard under IS: 12308 is being published to cover chemical analysis of cast iron and pig iron. This standard (Part 4) is one in the latter series. The other parts in the series are:

IS: 12308 Methods for chemical analysis of cast iron and pig iron

Part 1 Determination of total carbon by thermal conductivity method

Part 2 Determination of sulphur by iodimetric titration after combustion

Part 3 Determination of manganese by periodate spectrophotometric method

The method given in Part 4 has been prescribed on the basis of inter-laboratory tests carried by the various laboratories on standard samples of the respective materials.

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2: 1960 'Rules for rounding off numerical values (revised)'.

Indian Standard

METHODS FOR CHEMICAL ANALYSIS OF CAST IRON AND PIG IRON

PART 4 DETERMINATION OF TOTAL CARBON, GRAPHITIC CARBON AND COMBINED CARBON BY GRAVIMETRIC METHOD

1 SCOPE

1.1 This standard (Part 4) covers the gravimetric method for determination of total carbon, graphitic carbon and combined carbon in cast iron, alloyed cast iron and pig iron.

2 REFERENCE

IS 6626 (Part 1): 1971 Recommendations for apparatus for chemical analysis of metals; Part 1. Determination of carbon by direct combustion, is a necessary adjunct to this standard.

3 SAMPLING

- 3.1 The sample shall be drawn and prepared as prescribed in the relevant Indian Standard.
- 3.2 The sample is to be cleaned with analar grade organic solvent (like acetone, benzene or ether) by washing it thrice and dried in an air oven at 100 ± 5 °C.

4 QUALITY OF REAGENTS

Unless specified otherwise, analytical grade reagents and distilled water shall be employed in the test

5 DETERMINATION OF TOTAL CARBON, GRAPHITIC CARBON AND COMBINED CARBON BY GRAVIMETRIC METHOD

5.1 Outline of the Methods

5.1.1 Total Carbon

The sample is burnt in the presence of oxygen. The carbon dioxide formed is absorbed in a tube containing ascarite or soda asbestos and weighed.

5.1.2 Graphitic Carbon

The sample is dissolved in nitric acid and hydrofluoric acid. The graphitic carbon is filtered off in preignited asbestos in a fused silica gooch crucible and dried and ignited in a combustion furnace. Carbon dioxide so formed is absorbed in a tower of soda aspirate and weighed.

5.1.3 Combined Carbon

The difference between the percentage of total carbon and graphite carbon represents the combined carbon.

5.2 Reagents

- **5.2.1** Tower Packed with Granulated Manganese Dioxide
- 5.2.2 Tower Packed with Magnesium Perchlorate
- **5.2.3** Absorption Tower Packed with Soda Aspirate and Magnesium Perchlorate
- **5.2.4** Dilute Nitric Acid, 1:2(v/v)
- 5.2.5 Hydrofluoric acid, 40 percent
- **5.2.6** Preignited Asbestos for Gooch Crucible, (preserved in a desiccator)

5.3 Apparatus

The apparatus recommended in IS 6626 (Part 1): 1971 Recommendations for apparatus for chemical analysis of metals: Part 1 Determination of carbon by direct combustion may be used.

5.4 Procedure

5.4.1 For Total Carbon

Weigh 1.00 g of sample on a preignited combustion boat and introduce the same into the combustion tube maintained at a temperature of 1 100°C or above.

Stopper the combustion tube inside the furnace and allow the sample to heat for 1 to 2 minutes. Then pass oxygen at the rate of 800-1 000 ml per minute while combustion is going on and allow the evolved gases to pass through the tower of granular manganese dioxide and magnesium perchlorate and finally to the absorption tower (5.2.3) (tube A) kept in series. When the combustion is complete (about 2 minutes), reduce the rate of flow of oxygen to 400-500 ml/minute and continue for another 7-8 minutes in order to sweep off the carbon dioxide. Withdraw the absorption tower (tube A) filled with oxygen and place it in the balance case for 10 minutes,

IS 12308 (Part 4): 1988

open momentarily and weigh again and note the increase in mass of tube A.

Make a blank determination, following the same procedure and using the same amounts of all reagents except the sample.

5.4.1.1 Calculation

Total carbon

(percent) =
$$\frac{(A - B) \times 0.2729 \times 100}{C}$$

where

A = increase in mass (g) with the sample,

B =increase in mass (g) without the sample, and

C=mass in g of sample taken.

5.4.2 For Graphitic Carbon

Dissolve 1.00 g of sample in 50 ml of dilute nitric acid and heat on a water bath for 30 minutes. Add 1 to 2 drops of hydrofluoric acid and boil for 4 to 5 minutes. Remove from the

water bath and collect the residue by suction on ignited asbestos contained in fused silica Gooch crucible. Wash thoroughly with hot water, dry the residue at 150°C and determine the graphitic carbon by direct combustion at 1 000°C.

5.4.3 For Combined Carbon

The difference between total carbon and the graphitic carbon content represents the percentage of combined carbon. In case of alloyed cast iron, it is convenient to use a flux, such as red lead, or tin or vanadium pentoxide (free from carbon) to enhance the combustion.

5.5 Reproducibility

- a) For total carbon
 ± 0.07 at 2 percent carbon, and
 ± 0.1 at 4 percent carbon.
- b) For graphitic carbon
 ± 0.20 at 1 percent carbon, and
 ± 0.25 at 2 percent carbon.

Standard Mark

The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the Bureau of Indian Standards Act, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc: No. SMDC 2 (3102)

Amendments Issued Since Publication

Date of Issue	Text Affected
	Date of Issue

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002 Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha (Common to all Offices)

Regional Offices:	Telephone
Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{331 01 31 331 13 75
Eastern: 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola CALCUTTA 700054	36 2 4 9 9
Northern: SCO 445-446, Sector 35-C, CHANDIGARH 160036	[2 18 43

	J 2 10 45
	(3 16 41
Southern: C. I. T. Campus, IV Cross Road, MADRAS 600113	\[\begin{pmatrix} 41 24 42 \\ 41 25 19 \\ 141 29 16 \end{pmatrix}

BOMBAY 400093

Branches: AHMADABAD. BANGALORE, BHOPAL, BHUBANESHWAR

Western: Manakalaya, E9 MIDC, Marol, Andheri (East)

: AHMADABAD. BANGALORE, BHOPAL. BHUBANESHWAR GUWAHATI. HYDERABAD. JAIPUR. KANPUR. PATNA.

TRIVANDRUM.

6 32 92 95